

PRODUCT DATA SHEET

Dörr-Gardentop E-KV-4K-wf

Elastomeric Bitumen membrane with polyester fleece inlay as torch applied root resistant roofing & waterproofing

DESCRIPTION

Dörr-Gardentop E-KV-4K-wf (Thickness 4.0 mm) is a root resistant elastomeric bitumen membrane reinforced with a polyester fleece. The top side is with quartz sand finely granulated and the bottom side is laminated with a polyethylene torch-foil.

USES

Roofing and waterproofing membrane

- Green roof as cap layer
- Basement waterproofing for horizontal and vertical surfaces

FEATURES

- Elastic behaviour at low temperatures
- Robust, tear-resistant and stretchable reinforcement
- Root resistant and ecologically harmless
- High break down strength
- Chemically good compatible

CERTIFICATES AND TEST REPORTS

CE-Marking and declaration of performance to

- EN 13707 - Bitumen sheets for roof waterproofing

Resistance to root penetration – Institute of Horticulture, University of Applied Sciences Weihenstephan-Triesdorf

PRODUCT INFORMATION

Composition	coating	elastomeric bitumen root retardant
	reinforcement	polyester fleece
Packaging	single rolls	
Shelf life	no limitation Technical characteristics can be guaranteed for 24 months if stored properly	
Storage conditions	Store in a vertical position and protect from extreme external influence as such heat, cold, moisture etc.	
Appearance and colour	top	fine granule
	bottom	foil-laminated
Visible defects	free of visible defects	(EN 1850-1)
Length	10 m	(EN 1848-1)
Width	1 m	(EN 1848-1)

Thickness	4.0 mm	(EN 1849-1)
Straightness	< 20 mm / 10 m	(EN 1848-1)
Mass per area	4.8 kg/m ² [± 10%]	(EN 1849-1)

TECHNICAL INFORMATION

Resistance to impact	≥ 1.500 mm	(EN 12691 - A+B)
Resistance to static loading	≥ 20 kg	(EN 12730 - A+B)
Resistance to root penetration	passed	(EN 13948, FLL - procedure)
Tensile strength	maximum tensile force	(EN 12311-1)
	lengthwise	≥ 900 N / 50 mm
	crosswise	≥ 800 N / 50 mm
Elongation	elongation at maximum tensile force	(EN 12311-1)
	lengthwise	≥ 35 %
	crosswise	≥ 35 %
Tear strength	nail shank	(EN 12310-1)
	lengthwise	≥ 250 N
	crosswise	≥ 250 N
Joint shear resistance	shear resistance	(EN 12317-1)
	lengthwise	≥ 700 N / 50 mm
	crosswise	≥ 600 N / 50 mm
Dimensional stability	≤ 0.6 %	(EN 1107-1)
Flexibility at low temperature	-15 °C	(EN 1109)
Flow resistance	+100 °C	(EN 1110)
Watertightness	400 kPa	(EN 1928 - procedure B)
Water-vapour transmission rate	s _d = 320 m [± 20%]	(EN 1931 - procedure A)
Reaction to fire	class E	(EN 13501-1, EN 11925-2)

APPLICATION INFORMATION

Ambient air temperature	We recommend a minimum temperature of +5 °C during the application.
Substrate temperature	We recommend a minimum temperature of +5 °C during the application.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding or torching) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above

0,1 % (w/w).

APPLICATION INSTRUCTIONS

General provisions on substrate quality:

The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, oil, dust and loosely adhering particles.

Substrate preparation:

Use the appropriate preparation equipment to achieve the required substrate quality.

General provisions for the application:

Strictly follow installation procedures as defined in method statement, application manuals and working instructions which must always be adjusted to the actual site conditions.

All corresponding processing standards and regulations must be obeyed.

Protection:

The membrane must be protected from damage during any ongoing site activities.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Drr-GardentopE-KV-4K-wf-en-ATBIT-(06-2024)-2-1.pdf

PRODUCT DATA SHEET

Dörr-Gardentop E-KV-4K-wf

June 2024, Version 02.01

020920011990000363